


LR6-72PH 350~380M



Hi-MO1 High Efficiency Low LID Mono PERC Technology (1500V Compatible)



Complete System and Product Certifications

IEC 61215, IEC61730, UL1703

ISO 9001:2008: ISO Quality Management System

ISO 14001: 2004: ISO Environment Management System

TS62941: Guideline for module design qualification and type approval OHSAS 18001: 2007 Occupational Health and Safety





* Specifications subject to technical changes and tests. LONGi Solar reserves the right of interpretation.

Positive power tolerance (0 ~ +5W) guaranteed

High module conversion efficiency (up to 19.6%)

Slower power degradation enabled by Low LID Mono PERC technology: first year <2%, 0.55% year 2-25

Better energy yield with excellent low irradiance performance and temperature coefficient

Solid PID resistance ensured by solar cell process optimization and careful module BOM selection

Adaptable to harsh environment: passed rigorous salt mist and ammonia tests



Room 201, Building 8, Sandhill Plaza, Lane 2290, Zuchongzhi Road, Pudong District, Shanghai, 201203 Tel: + 86-21-61047332 Fax: +86-21-61047377 E-mail: module@longi-silicon.com Facebook: www.facebook.com/LONGi Solar

Note: Due to continuous technical innovation, R&D and improvement, technical data above mentioned may be of modification accordingly. LONGi Solar have the sole right to make such modification at anytime without further notice; Demanding party shall request for the latest datasheet for such as contract need, and make it a consisting and binding part of lawful documentation duly signed by both parties.

R6-72PH **350~380M**

Design (mm)

Units: mm Tolerance: Length: ±2mm Width: ±2mm Height: ±1mm Pitch=row: ±1mm A-A

Mechanical Parameters

Operating Parameters

Cell Orientation: 72 (6×12)

Junction Box: IP67, three diodes

Output Cable: 4mm², 1200mm in length

Connector: MC4 EVO2

Weight: 26.5kg

Dimension: 1956×991×45mm

Packaging: 23pcs per pallet

Power Output Tolerance: 0 ~ +5 W

Operational Temperature: -40 °C ~ +85 °C

Maximum System Voltage: DC1500V (IEC)

Maximum Series Fuse Rating: 20A

Nominal Operating Cell Temperature: 45±2 °C

Application Class: Class A


Electrical Characteristics Test uncertainty for F														ax: ±3%
Model Number	LR6-72PH-350M		LR6-72PH-355M		LR6-72PH-360M		LR6-72PH-365M		LR6-72PH-370M		LR6-72PH-375M		LR6-72PH-380M	
Testing Condition	STC	NOCT												
Maximum Power (Pmax/W)	350	257.3	355	260.9	360	264.6	365	268.3	370	272.0	375	275.6	380	279.3
Open Circuit Voltage (Voc/V)	47.5	43.9	47.7	44.1	47.9	44.3	48.0	44.4	48.3	44.7	48.5	44.9	48.7	45.0
Short Circuit Current (Isc/A)	9.57	7.71	9.63	7.76	9.70	7.82	9.74	7.85	9.84	7.93	9.90	7.98	9.99	8.05
Voltage at Maximum Power (Vmp/V)	38.8	35.6	39.0	35.9	39.2	36.0	39.3	36.1	39.4	36.2	39.6	36.4	39.8	36.6
Current at Maximum Power (Imp/A)	9.03	7.22	9.10	7.28	9.18	7.34	9.29	7.43	9.39	7.51	9.47	7.58	9.55	7.64
Module Efficiency(%)	18.1		18.3		18.6		18.8		19.1		19.3		19.6	

NOCT (Nominal Operating Cell Temperature): Irradiance 800W/m², Ambient Temperature 20 $^{\circ}\mathrm{C}$, Spectra at AM1.5, Wind at 1m/S


Temperature Ratings (STC) **Mechanical Loading** Temperature Coefficient of Isc +0.057%/°C Front Side Maximum Static Loading 5400Pa **Rear Side Maximum Static Loading** 2400Pa Temperature Coefficient of Voc -0.286%/°C **Hailstone Test** 25mm Hailstone at the speed of 23m/s **Temperature Coefficient of Pmax** -0.380%/°C

I-V Curve


Current-Voltage Curve (LR6-72PH-360M)



Power-Voltage Curve (LR6-72PH-360M)



Current-Voltage Curve (LR6-72PH-360M)





Room 201, Building 8, Sandhill Plaza, Lane 2290, Zuchongzhi Road, Pudong District, Shanghai, 201203 Tel: + 86-21-61047332 Fax: +86-21-61047377 E-mail: module@longi-silicon.com Facebook: www.facebook.com/LONGi Solar

Note: Due to continuous technical innovation, R&D and improvement, technical data above mentioned may be of modification accordingly. LONGi Solar have the sole right to make such modification at anytime without further notice; Demanding party shall request for the latest datasheet for such as contract need, and make it a consisting and binding part of lawful documentation duly signed by both parties.